

Product Information Sheet

FyreWrap[®] LiB G2 Coating

INTRODUCTION

FyreWrap[®] LiB (Lithium-ion Battery) G2 Coating from Alkegen is a high-temperature, lightweight flame barrier and electrically insulating material designed to increase safety and performance in lithium-ion battery packs. FyreWrap LiB G2 Coating utilizes the same core technologies as the FyreWrap LiB Films. The coating is easily applied at room temperature in atmospheric conditions.

FYREWAP LiB G2 COATING FEATURES

- Fire resistant, flame barrier
- Electrically insulating
- Proprietary fire blocking technology protects structures and substrates
- Variable thickness depending on the application
- Application via spraying or various types of roll coating
- High emissivity allows for greater heat dissipation

COATING CAPABILITIES

- Thermal runaway propagation prevention
- Short circuit prevention and electrical protection
- Cascading fire prevention
- Thermal isolation and containment

APPLICATIONS

- Cells (external to cell)
- Battery module
- Battery packs
- Packaging for transportation

MARKETS

- E-Mobility
- Energy Storage Systems (ESS)
- Aerospace
- Consumer Electronics
- Medical
- Transportation packaging



MATERIAL PROPERTIES

- Resistant to temperatures in excess of 1100°C
- Dielectric Strength (ASTM D149): 20 (kV/mm)*
- UL94 V-0*
- Thermal Conductivity (ASTM E1461) 0.199 W/m-K @ 25 °C
- Thickness: 0.05 mm to 0.5 mm thickness
- Basis Weight: 100 g/m² per 0.1 mm thickness
- Coverage Rate: 7.5 m²/Gallon @ 100 g/m²

ULTIMATE PROTECTION WITH FYREWAP LiB PERFORMANCE MATERIALS

Alkegen's purpose is based on a commitment to produce high-quality specialty products that help our customers save energy, reduce pollution and improve fire safety. Supporting and exemplifying the purpose statement, Alkegen is committed to delivering optimal solutions for fire, thermal and electrical safety within the lithium-ion battery pack. Please contact us to learn more about FyreWrap LiB Performance Materials.

FYREWAP LiB CAPABILITIES

- Thermal runaway propagation prevention
- Short circuit prevention and electrical protection
- Cascading fire prevention
- Thermal isolation and containment


Product Information Sheet

FyreWrap[®] LiB G2 Coating

FYREWAP LiB COATING APPLICATION STUDY

FyreWrap LiB G2 Coating was applied at a thickness of 0.1 mm on an aluminum panel that is 1 mm thick. The panel is pictured below on the right. The FyreWrap LiB Coated panel was exposed to a flame that was greater than 1000°C for 30 seconds. The aluminum panel showed no signs of deformation due to the flame protection provided by the coating technology. The same set-up shown below on the left, demonstrates the effects of not having the coating present on the panel. The flame melted the aluminum, causing a hole to form within seconds. The coating technology helps to maintain the structural integrity of the material while providing electrical protection in high temperature environments.

Based on recent testing, it is believed that the coating can withstand direct flame impingement in excess of five minutes**. To learn more about FyreWrap LiB G2 coating technologies or to discuss your application, please contact us at 716-768-6472.



Pictured above from left to right: Aluminum panel exposed to > 1000°C flame impingement, aluminum panel coated with 0.1mm FyreWrap LiB coating (no flame impingement), aluminum panel coated with 0.1 mm FyreWrap LiB coating after being impinged by a flame > 1000°C. Test set-up shown in greater detail in picture below.

*Testing was performed on coating applied to an aluminum panel.

**Duration of the prevention of flame penetration is dependent on many factors, including substrate thickness and type, coating thickness, velocity and temperature of flame, etc.

BARE ALUMINUM PANEL HEATED ABOVE 1000 °C



COATED ALUMINUM PANEL HEATED ABOVE 1000 °C



Please contact Alkegen for more information on FyreWrap LiB films and coatings along with any specific design requirements.

The following are registered trademarks of Alkegen: FyreWrap.

The test data shown are average results of tests conducted under standard procedures and are subject to variation. Results should not be used for specification purposes. Product Information Sheets are periodically updated by Alkegen. Before relying on any data or other information in this Product Information Sheet, you should confirm that it is still current and has not been superseded. A Product Information Sheet that has been superseded may contain incorrect, obsolete and/or irrelevant data and other information.

Form A-5260
Effective 07/23
© 2023 Alkegen
All Rights Reserved

Alkegen
Headquarters
5215 N. O'Connor Blvd, Suite 2300
Irving, TX 75039
Telephone: 716-768-6500
Website: www.alkegen.com
Email: batterygroup@alkegen.com